

Vydyne 50BW is a general-purpose PA66 resin designed for extrusion-compounding applications. It is offered in natural only and exhibits ideal white color and good color retention after compounding. This product is available at two moisture levels: 0.2% (max) as Vydyne 50BW and 0.5% (max) as Vydyne 50BWFS. Vydyne 50BW provides the chemical resistance typical of PA66 to many chemicals, machine and motor oils, solvents, and gasoline.

General

Regional Availability	• North America	• Europe	• Asia Pacific
Features	• Chemical Resistant • Good Color Stability	• Gasoline Resistant • Oil Resistant	• General Purpose • Solvent Resistant
Agency Rating	• ASTM, D4066 PA0111 • EU, 10/2011 • NSF, STD-51	• ASTM, D6779 PA0111 • EU, 2023/2006	• EC, 1935/2004 • FDA, 21 CFR 177.1500
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Other Extrusion		

Physical	dry	cond.	Unit	Test Standard
Density	1.14	-	g/cm ³	ISO 1183
Relative Viscosity, Sulphuric Acid	137 - 148		-	ISO 307
Relative Viscosity, Formic Acid	45 - 51		-	ASTM D 789
Moisture Content	0.2		%	ASTM D 6869
Yellowness Index	-4		YI	ASTM D 1925

Thermal	dry	cond.	Unit	Test Standard
Melting Temperature	260	*	°C	ISO 11357-3



North America
+1 888 927 2363

Europe
+32 10 608 600

Asia
+86 21 2315 0888

Disclaimer

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations makes no representation or warranties as to the completeness of accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purpose prior to use. In no event will Ascend Performance Materials Operations be responsible for damages of any nature whatsoever resulting in the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representation or warranties, either express or implied, of merchantability fitness for a particular purpose or of any other nature are made hereunder with respect to information or product to which information refers.

©2024 Ascend Performance Materials Operations. The Ascend Performance Materials name, brands, marks and logos (e.g., those identified with ®, ™, or SM) are owned by Ascend Performance Materials Operations, unless otherwise noted.

CAUTION: Do not use Ascend Performance Materials Operations MED grades in medical applications involving implantation in the human body or contact with internal body fluids or tissues for extended periods of time.